



Laboratory
Test

No. 364



Device:
QSun 3000



Total duration:
863h

**Unexposed area
(reference)**

**Exposed
area**



**Unexposed area
(reference)**

**Exposed
area**



LAB. ID NUMBER: 29619
POWDER COATING: DS-0834S
HEAT TRANSFER FILM: --
colour variation (ΔE): **0,88**
residual gloss: **95%**

LAB. ID NUMBER: 29621
POWDER COATING: DS-0834S
HEAT TRANSFER FILM: 2602/04
colour variation (ΔE): **2,7**
residual gloss: **99%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 863 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.