



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 12/08/2010

TO: 17/08/2011

LAB. ID NUMBER: 22485
POWDER COATING: DS 737
HEAT TRANSFER FILM: 2106/01L
colour variation (ΔE): 12,26
residual gloss: 35%

Technical Remarks

Residual gloss is very low and colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

