



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 15/06/2012

TO: 20/06/2013

LAB. ID NUMBER: 26678
POWDER COATING: DS-0407S
HEAT TRANSFER FILM: 6001/01
Colour variation (ΔE): **1,48**
residual gloss: **93%**

Technical Remarks

Excellent residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

