



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 18/03/2019

TO: 07/05/2020

LAB. ID NUMBER: 44256
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2117/07
Colour variation (ΔE): **2,78**
residual gloss: **83%**

Technical Remarks

Good residual gloss and sufficient colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.

**Unexposed area
(reference)**

**Exposed
area**

