



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 22/06/2012**

**TO: 21/06/2013**

LAB. ID NUMBER: 55425  
POWDER COATING: DS-1733S  
HEAT TRANSFER FILM: 1807/01  
Colour variation ( $\Delta E$ ): 1,4  
residual gloss: 95%

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

