



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 05/06/2009

TO: 04/06/2010

LAB. ID NUMBER: 18171
POWDER COATING: DS-0806S
HEAT TRANSFER FILM: 1001/09L
colour variation (ΔE): **2,44**
residual gloss: **94%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

