



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **07/08/2012**

TO: **06/08/2013**

LAB. ID NUMBER: 27443
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2505/02
Colour variation (ΔE): **1,69**
residual gloss: **94%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area
(reference)

Exposed
area

