



Florida Test



Total duration: 12 months



**EXPOSURE PERIOD:** 

FROM: 18/03/2019

> TO: 07/05/2020

LAB. ID NUMBER: 44078 POWDER COATING: DS-0752S HEAT TRANSFER FILM: 2507/13 Colour variation ( $\Delta E$ ): **5,41** residual gloss: 77%

## **Technical Remarks**

Residual gloss is excellent but colour variation is very high so not acceptable for outdoor use.

## **Technical opinion:**

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

## REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eyes.

