



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/11/2019

TO: 11/01/2021

LAB. ID NUMBER: 46231
POWDER COATING: DS 730
HEAT TRANSFER FILM: 2112/01
Colour variation (ΔE): **2,01**
residual gloss: 85%

Technical Remarks

Excellent residual gloss and sufficient colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.

