



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/11/2015**

**TO: 19/12/2016**

LAB. ID NUMBER: 55426  
POWDER COATING: DS 1704M  
HEAT TRANSFER FILM: 2501/05  
colour variation ( $\Delta E$ ): 1,92  
residual gloss: 75%

**Technical Remarks**

Good residual gloss and normal colour variation ( $\Delta E$ )

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

