



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/04/2019

TO: 09/05/2020

LAB. ID NUMBER: 51687
POWDER COATING: DS 1750
HEAT TRANSFER FILM: 1301/01
Colour variation (ΔE): **2,06**
residual gloss: **78%**

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

