



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 01/05/2021

TO: 01/05/2022

LAB. ID NUMBER: 55428
POWDER COATING: DS-0775MS
HEAT TRANSFER FILM: 2507/18
colour variation (ΔE): 1,89
residual gloss: 93%

Technical Remarks

Excellent residual gloss and normal colour variation
(ΔE)


Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye



**Unexposed area
(reference)**

**Exposed
area**