



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/04/2019

TO: 09/05/2020

LAB. ID NUMBER: 51291
POWDER COATING: 9F-250-A005
HEAT TRANSFER FILM: 1815/11
Colour variation (ΔE): 1,23
residual gloss: 94%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

