



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 12/08/2010**

**TO: 17/08/2011**

LAB. ID NUMBER: 22361  
POWDER COATING: DS 417  
HEAT TRANSFER FILM: 2505/02L  
colour variation ( $\Delta E$ ): 1,2  
residual gloss: 101%

#### **Technical Remarks**

Excellent residual gloss and very low colour variation  
( $\Delta E$ )

#### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

