



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **07/08/2012**

TO: **06/08/2013**

LAB. ID NUMBER: 27555
POWDER COATING: DS 721
HEAT TRANSFER FILM: 1402/02
Colour variation (ΔE): **1,95**
residual gloss: **64%**

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

Unexposed area
(reference)

Exposed
area

