



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 27/04/2019

TO: 07/05/2020

LAB. ID NUMBER: 44270
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2510/01
Colour variation (ΔE): **2,43**
residual gloss: 72%

Technical Remarks

Good residual gloss and normal colour variation (ΔE).


Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.



**Unexposed area
(reference)**

**Exposed
area**

