



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 13/10/2016**

**TO: 20/10/2017**

LAB. ID NUMBER: 40447  
POWDER COATING: DS 421  
HEAT TRANSFER FILM: 2108/08  
Colour variation ( $\Delta E$ ): **1,41**  
residual gloss: 77%

### Technical Remarks

Good residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

