



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 20/04/2015**

**TO: 09/05/2016**

LAB. ID NUMBER: 36906  
POWDER COATING: Glass-002  
HEAT TRANSFER FILM: 5026/02  
Grey Scale: 4  
residual gloss: 95%

**Technical Remarks**

Good residual gloss and low colour variation.

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.  
The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

