



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 19/01/2018**

**TO: 24/01/2019**

LAB. ID NUMBER: 41687  
POWDER COATING: DS 739  
HEAT TRANSFER FILM: 2515/01  
Colour variation ( $\Delta E$ ): 2  
residual gloss: 77%

**Technical Remarks**

Good residual gloss and normal colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

