



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 20/04/2015**

**TO: 09/05/2015**

LAB. ID NUMBER: 36917  
POWDER COATING: MirrorL-183S  
HEAT TRANSFER FILM: 2120/01  
Colour variation ( $\Delta E$ ): **7,41**  
residual gloss: **100%**

### **Technical Remarks**

Residual gloss is excellent but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

**Not for outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

