



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **23/05/2014**

TO: **27/05/2015**

LAB. ID NUMBER: 33926
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2301/03
Colour variation (ΔE): **2,36**
residual gloss: **78%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

