



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 19/01/2018

TO: 24/01/2019

LAB. ID NUMBER: 41701
POWDER COATING: DS 752
HEAT TRANSFER FILM: 1602/01
Colour variation (ΔE): **3,60**
residual gloss: 85%

Technical Remarks

Residual gloss is excellent but visual colour variation is not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

