



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 23/05/2014**

**TO: 27/05/2015**

LAB. ID NUMBER: 33930  
POWDER COATING: DS 733  
HEAT TRANSFER FILM: 2501/02  
Colour variation ( $\Delta E$ ): **2,59**  
residual gloss: **74%**

### **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).


### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).



**Unexposed area  
(reference)**

**Exposed  
area**

