



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 31/07/2023

TO: 22/08/2024

LAB. ID NUMBER: 54717
POWDER COATING: 9G-057-A005
HEAT TRANSFER FILM: 2118/04
Colour variation (ΔE): 0,83
residual gloss: 54%

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

