



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/04/2019**

**TO: 07/05/2020**

LAB. ID NUMBER: 44324  
POWDER COATING: DS 739  
HEAT TRANSFER FILM: 1301/03  
Colour variation ( $\Delta E$ ): **2,16**  
residual gloss: **81%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye.

