



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/04/2019**

**TO: 07/05/2020**

LAB. ID NUMBER: 44325  
POWDER COATING: DS 739  
HEAT TRANSFER FILM: 2304/02  
Colour variation ( $\Delta E$ ): **2,34**  
residual gloss: **76%**

**Technical Remarks**

Good residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye.

