



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 13/001/2011

TO: 17/01/2012

LAB. ID NUMBER: 23509
POWDER COATING: DS 734
HEAT TRANSFER FILM: 1202/01L
colour variation (ΔE): 1,65
residual gloss: 91%

Technical Remarks

Excellent residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

