



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: **20/12/2012**

TO: **02/01/2014**

LAB. ID NUMBER: 28640  
POWDER COATING: DS 725  
HEAT TRANSFER FILM: 2309/02  
Colour variation ( $\Delta E$ ): **1,44**  
residual gloss: **91%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

Unexposed area  
(reference)

Exposed  
area

