



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 19/01/2018**

**TO: 24/01/2019**

LAB. ID NUMBER: 41731  
POWDER COATING: DS 799  
HEAT TRANSFER FILM: 1406/01  
Colour variation ( $\Delta E$ ): 1,79  
residual gloss: 87%

### **Technical Remarks**

Excellent residual gloss and normal colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

