



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 10/08/2022**

**TO: 10/08/2023**

LAB. ID NUMBER: 50685  
POWDER COATING: DS 706  
HEAT TRANSFER FILM: 1803/01  
colour variation ( $\Delta E$ ): **1,93**  
residual gloss: **51%**

#### **Technical Remarks**

Sufficient residual gloss and normal color variation  
( $\Delta E$ )

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with  
the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

