



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 10/08/2022**

**TO: 10/08/2023**

LAB. ID NUMBER: 50862  
POWDER COATING: DS 734  
HEAT TRANSFER FILM: 2118/04  
colour variation ( $\Delta E$ ): 0,86  
residual gloss: 73%

### **Technical Remarks**

Good residual gloss and normal color variation ( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

