



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 30/04/2009

TO: 28/04/2010

LAB. ID NUMBER: 17582
POWDER COATING: DS 1733
HEAT TRANSFER FILM: 1406/01L
colour variation (ΔE): 2,21
residual gloss: 75%

Technical Remarks

Excellent residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

