



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 20/04/2015**

**TO: 09/05/2016**

LAB. ID NUMBER: 36702  
POWDER COATING: DS 708  
HEAT TRANSFER FILM: 5001/01  
Colour variation ( $\Delta E$ ): 0,79  
residual gloss: 100%

#### **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ )

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

**Unexposed area  
(reference)**

**Exposed  
area**

