Test Report: Florida Natural Exposure



144





Total duration: 12 months



EXPOSURE PERIOD:

FROM: 10/08/2022 TO: 10/08/2023

LAB. ID NUMBER: 52902 POWDER COATING: DS 746 HEAT TRANSFER FILM: 2602/04 colour variation (ΔE): **0,95** residual gloss: **51**%

Technical Remarks

Sufficient residual gloss and low color variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

