Test Report: Florida Natural Exposure



144

Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 31/07/2023 TO: 22/08/2024

LAB. ID NUMBER: 54843 POWDER COATING: DS 733 HEAT TRANSFER FILM: 2501/05 Colour variation (ΔE): **1,20** residual gloss: **58**%

Technical Remarks

Sufficient residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

