



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/04/2019**

**TO: 07/05/2020**

LAB. ID NUMBER: 44365  
POWDER COATING: DS 797  
HEAT TRANSFER FILM: 1412/05  
Colour variation ( $\Delta E$ ): 2  
residual gloss: 68%

**Technical Remarks**

Sufficient residual gloss and low colour variation ( $\Delta E$ ).


**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye.



**Unexposed area  
(reference)**

**Exposed  
area**

