

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 27/04/2019

TO: 07/05/2020

LAB. ID NUMBER: 44370
POWDER COATING: Mirror-107S
HEAT TRANSFER FILM: 6047/03
Colour variation (ΔE): **1,41**
residual gloss: **99%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.

