



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/08/2013

TO: 21/08/2014

LAB. ID NUMBER: 31992
POWDER COATING: DS 734
HEAT TRANSFER FILM: 5001/02
Colour variation (ΔE): 0,75
residual gloss: 90%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

