

Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 20/04/2015

TO: 09/05/2016

LAB. ID NUMBER: 36724
POWDER COATING: DS 733M4
HEAT TRANSFER FILM: 1803/01
Colour variation (ΔΕ): **2,74**residual gloss: **90**%

## **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ )


## **Technical Opinion:**

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

## QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss. The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).



Date: 26/09/2016