



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 19/01/2018

TO: 24/01/2019

LAB. ID NUMBER: 41808
POWDER COATING: MirrorBT-058S
HEAT TRANSFER FILM: 5014/08
Colour variation (ΔE): 1,85
residual gloss: 92%

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

