



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 04/06/2020

TO: 04/06/2021

LAB. ID NUMBER: 46800
POWDER COATING: DS 772
HEAT TRANSFER FILM: 2531/02
Colour variation (ΔE): **1,58**
residual gloss: **68%**

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

