



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/11/2019

TO: 11/01/2021

LAB. ID NUMBER: 46197
POWDER COATING: DS-0730S
HEAT TRANSFER FILM: 2203/03
colour variation (ΔE): 1,57
residual gloss: 94%

Technical Remarks

Excellent residual gloss and normal colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

