



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/11/2019

TO: 11/01/2021

LAB. ID NUMBER: 46263
POWDER COATING: DS 704M
HEAT TRANSFER FILM: 5014/06
colour variation (ΔE): **0,49**
residual gloss: **51%**

Technical Remarks

Sufficient residual gloss and normal colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

