



Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 10/08/2022

TO: 10/08/2023

LAB. ID NUMBER: 52872 POWDER COATING: DS-0734S HEAT TRANSFER FILM: 2117/10 colour variation (Δ E): 1,81 residual gloss: 92%

Technical Remarks

Excellent residual gloss and normal color variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

