

 **Florida  
Test**

 **Total duration:  
12 months**

 **EXPOSURE PERIOD:**

**FROM: 10/08/2022**

**TO: 10/08/2023**

LAB. ID NUMBER: 52585  
POWDER COATING: DS 733  
HEAT TRANSFER FILM: 2902/04  
colour variation ( $\Delta E$ ): 1,47  
residual gloss: 51%

**Technical Remarks**

Sufficient residual gloss and normal color variation ( $\Delta E$ )

**Technical Opinion:**  
**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**  
The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

