



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/04/2015

TO: 09/05/2016

LAB. ID NUMBER: 36774
POWDER COATING: 8G-038-A002
HEAT TRANSFER FILM: 5026/05
Colour variation (ΔE): **9,68**
residual gloss: 75%

Technical Remarks

Residual gloss is sufficient but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

