



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 31/07/2023

TO: 22/08/2024

LAB. ID NUMBER: 54761
POWDER COATING: DS 716
HEAT TRANSFER FILM: 2505/10
Colour variation (ΔE): **1,55**
residual gloss: **78%**

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

