



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 20/04/2015**

**TO: 09/05/2016**

LAB. ID NUMBER: 36775  
POWDER COATING: 8G-039-A002  
HEAT TRANSFER FILM: 2121/02  
Colour variation ( $\Delta E$ ): **4,83**  
residual gloss: **63%**

#### **Technical Remarks**

Residual gloss is sufficient but colour variation is very high so not acceptable for outdoor use.

**Technical opinion:**

**Not for outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

