



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 14/01/2012**

**TO: 16/01/2013**

LAB. ID NUMBER: 25418  
POWDER COATING: DS 421  
HEAT TRANSFER FILM: 2531/02L  
colour variation ( $\Delta E$ ): 1,90  
residual gloss: 103%

### **Technical Remarks**

Excellent residual gloss and very low colour variation  
( $\Delta E$ )

### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

