Test Report: Florida Natural Exposure



## 160

Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 10/08/2022 TO: 10/08/2023

LAB. ID NUMBER: 52459 POWDER COATING: DS 704M HEAT TRANSFER FILM: 5014/10 colour variation ( $\Delta E$ ): 0,69 residual gloss: 51%

## **Technical Remarks**

Sufficient residual gloss and low color variation ( $\Delta E$ )

## Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

## REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

